



Product Specification Sheet				
Product Name:	MAT 14 SCR/SRS			
Product Description	Semi-Re bonded Magnesia Chrome bricks			
Application	PSC Tuyere Area			
Chemical Properties	Unit	Values		Testing Method
		STANDARD		
MgO	%	≥ 55		XRF & GB/T5070-2007
Cr2O3	%	≥ 24		
SiO2	%	≤ 1.0		
Al2O3	%	≤ 7.2		
CaO	%	≤ 0.9		
Fe2O3	%	≤ 11		
A.P.,	%	≤ 16		ISO 5017:1998
Bulk Density	g/cm3	≥ 3.25		ISO 5017:1998
CCS	MPa	≥ 55		ISO 10059-2 2003
RUL 0.2MPa/T0.6	°C	≥ 1750		ISO1893:2005
<b>Dimensional Tolerance</b>	mm			
≤100mm	+/-1	Warpage %		0.5 max
101-200mm	+/-1.5	Edge Breach (a+b+c)		≤60mm, no more than 3 positions
201-300mm	+/-2	Corner Breach (e+f+g)		≤40mm, no more than 3 positions
≥300mm	+/-2.5			

The Technical Data in this publication is given for guidance only. Whilst every care is taken in the preparation of these figures, they are approximate and should not be used for specification purposes.